

FIBONACCI STONE

Technical Data & Test Results - RIVERSTONE

Binder Portland Cement Type 1

Water/Cement Ratio 0.32

Maximum Aggregate Size 6mm

STANDARD APPLIED/ TEST	RESULT
-----------------------------------	---------------

UNI-10444 Specific Weight	2.25
-------------------------------------	------

UNI-10444 Water Absorption by Weight (%)	2.9%
--	------

UNI-6133 Flexural Strength (N/mm ²)	14
---	----

UNI-10532 Resistance to Deep Abrasion (mm ³)	400
--	-----

DIN-52104 Resistance to Freeze/Thaw	Resistant
---	-----------

DIN-52105 Compressive Strength (N/mm ²)	105
---	-----

ISO/DIS 1182.2 Resistance to Fire	Class 0
---	---------

FIBONACCI STONE

Summary of Slip Resistance Tests Performed and Classification

RIVERSTONE – POLISHED	CLASS
------------------------------	--------------

AS/NZ 4586:2004 – Slip resistance classification of new pedestrian surface materials. Appendix A: WET Pendulum (Four S slider):	Z
---	----------

RIVERSTONE – HONED	CLASS
---------------------------	--------------

AS/NZ 4586:2004 – Slip resistance classification of new pedestrian surface materials. Appendix A: WET Pendulum (Four S slider):	W
---	----------

AS/NZ 4586:2004 – Slip resistance classification of new pedestrian surface materials. Appendix D: OIL-WET Ramp	R9
--	-----------

AS/NZ 4586:2004 – Slip resistance classification of new pedestrian surface materials. Appendix C: WET/BAREFOOT Ramp	B
---	----------

RIVERSTONE – SANDBLASTED	CLASS
---------------------------------	--------------

AS/NZ 4586:2004 – Slip resistance classification of new pedestrian surface materials. Appendix A: WET Pendulum (Four S slider):	V
---	----------

AS/NZ 4586:2004 – Slip resistance classification of new pedestrian surface materials. Appendix D: OIL-WET Ramp	R13
--	------------

AS/NZ 4586:2004 – Slip resistance classification of new pedestrian surface materials. Appendix C: WET/BAREFOOT Ramp	C
---	----------

In order to interpret the classifications, please refer to Standards Australia Handbook 197, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum for a wide variety of locations.

It is important to realize that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.